

15

1. A method of manufacturing a semiconductor device having a plurality of gate insulating films of different thicknesses on a semiconductor substrate, comprising the steps of:

injecting fluorine into a region of a semiconductor substrate other than a region of the semiconductor substrate where a thinnest gate insulating film is to be formed, among a plurality of regions where gate insulating films are to be formed;

oxidizing the semiconductor substrate with fluorine injected therein to form an oxide film in said plurality of regions; and

nitriding a surface of said oxide film to turn a surface layer thereof into an oxynitride film or form a nitride film on the surface of said oxide film.

- 2. A method according to claim 1, wherein said step of injecting fluorine comprises the step of:
- setting conditions for injecting fluorine such that the gate insulating films formed on said semiconductor substrate have a thickness of at least 0.2 nm.
- 3. A method according to claim 1, wherein said step

  of nitriding the surface of said oxide film further comprises
  the step of:

15

introducing radical nitrogen excited by plasma into the surface of said oxide film.

4. A method of manufacturing a semiconductor device having a plurality of gate insulating films of different thicknesses on a semiconductor substrate, comprising the steps of:

forming a first oxide film on a surface of a semiconductor substrate;

removing said first oxide film from regions of the semiconductor substrate other than a region of the semiconductor substrate where a thickest gate insulating film is to be formed, among a plurality of regions where gate insulating films are to be formed;

injecting fluorine into the region other than the region where a thinnest gate insulating film is to be formed, among the regions of the semiconductor substrate from which said first oxide film has been removed;

oxidizing the semiconductor substrate with fluorine injected therein to form a second oxide film in said plurality of regions; and

nitriding a surface of said second oxide film to turn a surface layer thereof into an oxynitride film or form a nitride film on the surface of said second oxide film.

5. A method according to claim 4, wherein said step

25

20

25

of injecting fluorine comprises the step of:

setting conditions for injecting fluorine such that the gate insulating films formed on said semiconductor substrate have a thickness of at least 0.2 nm.

6. A method according to claim 4, wherein said step of nitriding the surface of said second oxide film further comprises the step of:

introducing radical nitrogen excited by plasma

10 into the surface of said second oxide film.

7. A method of manufacturing a semiconductor device having a plurality of gate insulating films of different thicknesses on a semiconductor substrate, comprising the steps of:

forming a first oxide film on a surface of a semiconductor substrate;

forming a first polysilicon film on a surface of said first oxide film;

removing said first polysilicon film and said first oxide film from regions of the semiconductor substrate other than a region of the semiconductor substrate where a thickest gate insulating film is to be formed, among a plurality of regions where gate insulating films are to be formed;

injecting fluorine into the region other than the region where a thinnest gate insulating film is to be formed,

on the contract of the contrac

among the regions of the semiconductor substrate from which said first polysilicon film and said first oxide film have been removed;

oxidizing the semiconductor substrate with fluorine injected therein to form a second oxide film in said plurality of regions;

nitriding a surface of said second oxide film to turn a surface layer thereof into an oxynitride film or form a nitride film on the surface of said second oxide film;

forming a second polysilicon film on a surface of , said oxynitride film or a surface of said nitride film; and

removing a structure above said first polysilicon film from the region where the thickest gate insulating film is to be formed, among said plurality of regions.

8. A method according to claim 7, wherein said step of injecting fluorine comprises the step of:

setting conditions for injecting fluorine such that the gate insulating films formed on said semiconductor substrate have a thickness of at least 0.2 nm.

- 9. A method according to claim 7, wherein said step of nitriding the surface of said second oxide film further comprises the step of:
- into the surface of said oxide film.

15

20

10

10. A semiconductor device having a plurality of gate insulating films of different thicknesses including at least an oxide film on a surface of a semiconductor substrate, comprising:

a semiconductor substrate;

a plurality of oxide films formed respectively in different regions in a surface of said semiconductor substrate to respective different thicknesses; and

a plurality of oxynitride films or nitride films, produced by nitriding surfaces of said oxide films.

- 11. A semiconductor device according to claim 10, wherein said oxynitride films or nitride films are formed on the surfaces of the oxide films other than the thickest oxide film.
- 12. A semiconductor device according to claim 10, wherein the thicknesses of said oxide films are different from each other by at least 0.2 nm.